

Magnetization Effect of Pressure Gage Block

Masayoshi Wake
Fermilab, TS/Mag.R&D
January 31, 1991

The preloading of the SSC magnet coil is measured by the bending of a beam installed in the collar. This material is known to have small magnetization. A measurement of the remanent field was made using Rawson-Lush type 789 field probe in the study of "periodic field" in DSA321 50 mm dipole magnet. Figure 1. is the observed magnetic field as a function of axial position. The plot is indicated with subtraction of current-produced field assuming transfer function is $10.30G/A$.

The field has a clear bump at the position of the pressure gage. Magnetization increases when the current of the magnet is increased. The change of the field pattern is shown in the figure. The arrow attached to the current indicates the direction of the ramp going up or down. Since the back ground field of this magnetization also behaves nonlinearly, the magnetization effect of the gage block is measured as the difference of the field to the other part of the magnet.

Figure 2 shows the magnetization effect of the gage block extracted from the change of the field pattern. It seems like having tendency of saturation. Probably the disturbance to the field will be about 40 gauss for the injection field. A little surprise is that the magnetization goes away if the magnet is quenched. This could be due to either a temperature rise of the gage block to disorder the ferro-magnetism or an eddy current which produces a demagnetization field.

Distribution:

Bill Boroski
Rodger Bossert
Rod Crockett
Steve Delchamps
Mike Gordon
Steve Gourlay
Ray Hanft
Tariq Jaffery

Moyses Kuchnir
Mike Lamm
Paul Mantsch
Gale Pewitt
Dick Sims
Jim Strait
Gianni Tassotto
Masayoshi Wake
Mike Winters

DSA321 Remanent Field




Fig. 1




Fig. 2